

Description

Total Thickness:	2.0 mils (nominal)
Adhesive:	100% Dow Acrylic PS Adhesive
Color:	Clear

Physical Properties

Tensile Strength (lbs/in):	27	PSTC-131*	(ASTM D3759**)
Elongation (% at break):	140	PSTC-131	(ASTM D3759)
180° Peel Adhesion (oz/in):	24	PSTC-101	(ASTM D3330***)
Resistance to UV Lighting:		Excellent	

Application Temperature

32°F to 140°F

Operating Temperature

-10°F to 200° F

Typical Applications

For use in office or mailroom environments where added noise is undesirable. For sealing light to moderate weight cartons.

Other Standards and Specifications

Conforms to FDA SPECS: 21 CFR 175.105 and CFR 177.1520
Complies with environmental considerations of ASTM D 1974-14

Application and Operating Conditions

*Pressure Sensitive Tape Council

**ASTM Standard D3759, "Standard Test Method for Tensile Strength and Elongation of Pressure-Sensitive Tapes"

***ASTM Standard D3330, "Standard Test Method for Peel Adhesion of Pressure Sensitive Tapes"