

Product Description

Total Thickness:	1.9 mils (nominal)
Adhesive:	Synthetic Rubber Hot Melt
Color(s):	Clear

Physical Properties

Tensile Strength (lbs/in):	24	PSTC-131*	(ASTM D3759**)
Elongation (% at break):	140	PSTC-131	(ASTM D3759)
180° Peel Adhesion (oz/in):	36	PSTC-101	(ASTM D3330***)
Resistance to UV Lighting:		Fair	

Application Temperature

32° to 120° F

Operation Temperature

-10° to 120° F

Typical Applications

For sealing moderate weight cartons subjected to normal shipping conditions in a wide range of temperatures where quick tack, fast production hot melt adhesive is desired.

Other Standards and Specifications

Complies with environmental considerations of ASTM D 1974-14

Application and Operating Conditions:

*Pressure Sensitive Tape Council

**ASTM Standard D3759, "Standard Test Method for Tensile Strength and Elongation of Pressure Sensitive Tapes"

***ASTM Standard D3330, "Standard Test Method for Peel Adhesion of Pressure Sensitive Tapes"